THE INTERNATIONAL GROUP, INC.

85 Old Eagle School Road · P.O. Box 384 · Wayne, PA 19087 · (610) 687-9030 · Fax (610) 254-8548 50 Salome Drive · Agincourt, Ontario, Canada M1S 2A8 · (416) 293-4151 · Fax (416) 293-0344

PARAFFLEX® 4786

PARAFFLEX[®] **4786** is a specialty formulation of petroleum derived waxes specifically modified for use in the manufacture of container candles. PARAFFLEX[®] 4786 is a hard, smooth, opaque and creamy blend that shows up color well.

PHYSICAL PROPERTIES

	ASTM	SPECIFICATIONS		
TEST METHODS	METHOD	Minimum	Maximum	TYPICAL
Melt Point °F (°C)	D 87	120 (48.9)	129 (53.9)	124 (51.1)
Kinematic Viscosity, cSt @ 210°F (98.9°C)	D 445	2.9	5.4	4.0
Saybolt Viscosity, SUS @ 210°F (98.9°C)	D 2161	35.9	44.0	39.5
Oil Content, Wt%	D 721		2.5	2.0
Flash Point (P.M.), °F (°C)	D 93			380 (193)
Saybolt Color	D 156	+15		+20
Needle Penetration, dmm @ 77°F (25°C)	D 1321		50	36
API Gravity	D 287			41.5

FDA STATUS:

This product meets the FDA requirements set forth in 21 CFR 178.3850 for use in contact with food.

7/31/03

WARRANTY DISCLAIMER STATEMENT

The information contained in this bulletin is based on tests which are believed to be reliable. As actual conditions of use may vary and are beyond the control of THE INTERNATIONAL GROUP, INC. the product's specified characteristics cannot be guaranteed and are offered solely for the buyers evaluation and verification. There are no warranties, representations or conditions, expressed or implied, of any kind, including, but limited to, merchantability or fitness for a particular purpose made by THE INTERNATIONAL GROUP, INC. or its officers, employees or affiliates, in connection with the sale of the products described in this bulletin. Accordingly, the purchaser and each user assumes all risks and liability in connection with their use of such products. Nothing contained herein is to be construed as permission, recommendation or inducement by THE INTERNATIONAL GROUP, INC. or its officers, employees or affiliates, to use any product or process so as to infringe or conflict with any patent. Further, it is the user's obligation to utilize this material in full compliance with health, safety and environmental regulations. THE INTERNATIONAL GROUP, INC. recommends that the Material Safety Data Sheet for this product be consulted prior to handling.