

## Product Data Sheet

### EcoSoya Q220

#### Product Description

Soy wax.

#### Technical Properties

Analysis	Typical	Method
Mettler Drop Point	117F (47.2C)	AOCS Cc 18-80
Congealing Point	109F (42.8C)	ASTM D 938-60
Needle Penetration (1/10 mm)	45	ASTM D 1321-65
Color, Red	3.0	AOCS Cc 13b-45

#### Suggested Applications/Possible Uses

Container Candles, Pillar Candles, Molded Candles, Tarts, Melts and other applications.

#### Shelf Life

##### Packaged Product

No determined shelf life if stored under proper conditions.

##### Liquid Bulk Product

Two to four weeks under proper storage conditions.

#### Shipping and Storage

##### Packaged Product

Store in a cool, dry location away from direct heat, sunlight, and moisture. Temporary hot or cold temperature extremes have no adverse effect. EcoSoya waxes may be used frozen and, if partially melted, allow to cool, and re-solidify before use.

##### Liquid Bulk Product

Bulk oil should be shipped under a nitrogen blanket and have no contact with brass or copper. For storage, oil should be kept just above the melting point with no agitation, under nitrogen blanket, and have no contact with brass or copper.

**EcoSoya Brands, LLC | [www.ecosoyabrands.com](http://www.ecosoyabrands.com) | Tel: 1-865-690-4155**

The information presented herein is believed to be accurate and reliable under US law. All statements, recommendations or suggestions are made without warranty or guarantee, express or implied, and are subject to change without notice. We disclaim all liability in connection with the use of the products or information contained herein.